

LG HAUSYS FLOORS' SEAMING OPTIONS - NATURELIFE™, ARTWALK™

Heat welding produces the strongest seams, when two grooved edges are thermally fused together correctly. Heat welding is the recommended seaming method for NATURELIFE™. Heat welding is an option with ARTWALK™.

Chemical-Weld Seam Sealer

LG Hausys Floors' Chemical-Weld Seam Sealer is an option with NATURELIFE™.

LG Hausys Floors' Chemical-Weld Seam Sealer is the recommended seaming method for ARTWALK™.

LG Hausys Floors' Chemical-Weld Seam Sealer is available in kits including plastic applicator bottle. Each kit contains two 25 gram bottles of seam sealer and 1 plastic applicator bottle. Two 25 gram bottles of seam sealer will fill one plastic applicator bottle and cover approximately 150 linear feet of seam. Special shipping and handling is required for this product. Please follow directions found in the current LG Hausys Floors Installation Guide at www.lghausys.com

Chemical sealed seams produce excellent results if done correctly as well. The problem is the craftsmanship required to make a quality seam between two edges is often lost in today's fast paced job site.

- No adhesive can contaminate the seam.
- Both edges of the sheet vinyl must be clean, to allow a chemical bond.
- Edges must be parallel, with no gapping.
- Edges can't be so tight they pucker upward.
- Any narrow line of sealer left on the surface must be uniform.

LG Hausys Floors Tech Support:

1- 800 - 241-2073

www.lghausys.com

